

Application No.: 10/683,851
Filing Date: October 10, 2003
Page: 2

Amendments to the Claims

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1. (Currently Amended) A biaxially oriented polyester film having a base layer B, which is composed of at least 80% by weight of a thermoplastic polyester, and having two outer layers A and C, wherein the outer layer A has a surface smoothness, $R_a \leq [[28]]$ 21 nm, and the outer layer C comprises external particles and has, per mm² of film surface area, a number N_c of elevations whose respective heights h are correlated via the following equation

$$\begin{aligned} A_{h1} - B_{h1} \cdot \log_{10} h / \mu\text{m} &\leq \log_{10} (N_c / \text{mm}^2) \\ 0.01 \mu\text{m} &\leq h \leq 1 \mu\text{m} \\ A_{h1} &= 0.05; \quad B_{h1} = 3.3 \end{aligned} \quad (1)$$

wherein the outer layer A comprises no external particles and the gloss (20°) of the uncoated surface layer A is greater than 190.

2. (Original) The polyester film as claimed in claim 1, wherein the polyester of the base layer B contains units of ethylene glycol and terephthalic acid, and/or units of ethylene glycol and naphthalene 2,6-dicarboxylic acid.

3. (Original) The polyester film as claimed in claim 1, wherein the polyester used in the base layer B comprises polyethylene terephthalate.

4. (Canceled) Please cancel Claim 4.

Application No.: 10/683,851
Filing Date: October 10, 2003
Page: 3

5. (Original) The polyester film as claimed in claim 1, wherein the external particles present in the outer layer C comprise antiblocking agents or pigments.

6. (Original) The polyester film as claimed in claim 1, wherein the antiblocking agents present in the outer layer C comprise SiO₂.

7. (Original) The polyester film as claimed in claim 1, wherein the external particles of the outer layer C have an average primary particle diameter smaller than 50 nm and/or an average primary particle diameter of from 1 to 4 μm .

8. (Original) The polyester film as claimed in claim 1, wherein the outer layer C comprises the external particles at a concentration of from 0.1 to 0.5% by weight, based on the weight of the layer C.

9. (Original) The polyester film as claimed in claim 1, wherein the planar orientation of the film is greater than 0.163.

10. (Canceled) Please cancel Claim 10.

11. (Original) The polyester film as claimed in claim 1, which has an A-B-C layer structure.

12. (Currently Amended) The polyester film as claimed in claim 1, wherein the film further comprises a coating disposed on the outer layer A, said coating formed by the a CVD or PECVD process, wherein said film has an oxygen transmission smaller than 3 $\text{cm}^3/(\text{m}^2 \cdot \text{bar} \cdot \text{d})$.

13. (Original) The polyester film as claimed in claim 1, the outer layer A of which has been coated, using plasma-polymerized hexamethyldisiloxane or CH₄.

Application No.: 10/683,851
Filing Date: October 10, 2003
Page: 4

14. (Original) A process for producing a polyester film as claimed in claim 1, encompassing the steps of
- a) producing a multilayer film by extrusion or coextrusion and shaping the melts to give flat melt films
 - b) stretching the film biaxially, and
 - c) heat-setting the stretched film.
15. (Original) Packaging film formed from polyester film in accordance with claim 1.